

## STC

# ONE-COMPONENT CLEAR SEALANT

- · Crystal clear sealant
- Non-yellowing excellent resistance to UV
- · Environmentally friendly
- Free of isocyanates and solvents no hazard symbols
- No bubble formation
- Permanently flexible over a wide range of temperatures



### Notice

All information including images are given with the greatest care. Still, it is appropriate to users regardless of the test the suitability of each product for their own purposes. Tech-Masters is not liable for the completeness and accuracy of information and refuses warranty for your specific use. The guarantee, which Tech-Masters products provide, relates only to the standard conditions of sale of this product. In no case Tech-Masters can be held responsible for incidental damages, or damages for improper use or sale of the product to another customer.

# **SEAL TECH CRYSTAL**

#### **General Information**

SEAL TECH CRYSTAL is one component, non-sagging, elastic SiMP (Silyl Modified Polymer) adhesive. It cures under the influence of atmospheric moisture to form a high performance, permanently flexible elastic sealant.

SEAL TECH CRYSTAL is solvent- and isocyanate free and has no VOC.

SEAL TECH CRYSTAL is odourless and does not form bubbles during and after application. It is perfectly resistant to UV rays and is non-yellowing.

#### **Technical Information**

Form: non-sag thixotropic paste Colour: crystal clear Chemical nature: SiMP - Silv! Modif

Chemical nature: SiMP - Silyl Modified Polymer Curing mechanism: moisture-curing Curing through volume (at 23°C and 50% RH):

approx. 3,2mm

Shore Hardness A (DIN 53505): approx. 44 N/mm<sup>2</sup> Relative density: 1,04 - 1,08 (ISO 1183-1 A) Tack-free time (at 23°C and 50% RH): approx. 35 min Elastic modulus at 100% (ISO 37 DIN 53504): approx. 1,4 N/mm<sup>2</sup>

Dynamic viscosity: 6000 - 95000 Pa\*s (UNI EN ISO 3219

- Rotational viscometer)

Tensile strength (ISO 37 DIN 53504):

approx. 2,8 N/mm²

Elongation (ISO 37 DIN 53504): approx. 230%

Application temperature: -5°C - +40°C

Temperature resistance:

-40°C/+80°C, with brief point at +120°C Shelf life: 12 months in its original packaging (unopened)

Storage: at 5°C - 25°C in a cool, dry place; keep away from wet areas, direct sunlight and heat sources

### **Application and Use**

- · APPLICATION:
- Crystal clear sealing and bonding between differnt materials
- Elastic bonding between metal, plastic, glass and other materials
- Sealing joints in vertical and horizontal applications
- High mechanical/dynamic stress resistance shock/impact resistance
- Increase torsional stiffness of final assembly
- Vibration and sound damping bonding - Suitable for indood and outdoor use

- USE
  - Surface to be treated must be clean, dry and free from dust and grease
  - Primers may be required on some substrates and in certain application cycles
  - May be painted over (make a compatability test beforehand)
- Drying time of alkyd resin based paint may increase























