

WPU

ZINC PHOSPHATE PRIMER FOR DURABLE CORROSION PROTECTION

- Zinc containing coating
- Excellent corrosion protection
- Highly cohesive coating film, excellent adhesion
- Good sand ability
- Can be used on all metal surfaces
- Over paintable with most modern paints and coatings



WELD PRIMER ULTRA

General Information

WELD PRIMER ULTRA is a high-quality welding primer which provides excellent corrosion protection. Due to the excellent adhesion of WELD PRIMER ULTRA, the risk

of corrosion and rust formation is drastically reduced. It can be effortlessly applied to the surfaces to be protected and dries quickly.

Technical Information

Base: Zinc phosphate, talcum, titanium dioxide, carbon black, modified alkyd resins
 Colour: Red-brown
 Physical state: Aerosol
 Odeur: Solvents
 Salt Spray Test (DIN 50021 + DIN53210): 80 mu 250 hours à Ri0
 Boiling point: -44.5°C
 Lower and upper explosion limit:
 - Lower: 0.6 Vol%
 - Upper: 13 Vol%
 Flash point: -97°C
 Ignition Temperature: 365°C
 Weldable: after 15 minutes at 20 °C (max. layer 30 mu)

Overpaintable: after 8 hours
 pH: Mixture is non-polar/aprotic.
 Vapour pressure (at 20°C): 2100 hPa
 Pressure (at 20°C): 3.1 bar
 Density (at 20°C): 0.748 g/cm³
 Organic solvents: 80.2%
 Solids content: 20.4%
 Pressure (at 20°C): 3.1 bar
 Delivery rate (at 20°C): 1.5 g/sec
 Recommended operating / temperature range: -50°C - 100°C
 Peak temperature: 130°C
 Application temperature: 10°C - 25°C
 Storage conditions: Cool (10°C - 20°C) and dry

Application and Use

- APPLICATION:
 - Metal processing, heavy industry, shipbuilding, automotive industry
 - Typical applications include touching up ferrous metal parts after welding and to provide long-term protection of metal assemblies
 - The weldable primer creates a highly effective and durable rust protection layer and is applied before the welding process to prime areas that are no longer accessible afterwards.
- USE:
 - Surface preparation: Derust, sand and clean the surfaces to be painted. If necessary, apply filler to correct rough unevenness.
 - Shake WELD PRIMER ULTRA: Shake the primer for at least 2 minutes before use to ensure even distribution of ingredients.
 - Apply WELD PRIMER ULTRA: Spray on from a distance of approx. 25 cm. Level small dents and porous repair areas by repeatedly spraying thin coats and sanding. Take care to create an even layer and distribute the primer evenly.
 - Note: Carefully read and observe the warnings on the label before use!

| Article nr | Name | Content | Shelf Life | Catalog |
|------------|-------------------------|---------|-------------------------|----------------------------------|
| T903500 | Weld Primer Ultra 500ml | 500ml | see imprint + 12 months | SURFACE PROTECTION AND TREATMENT |



Notice

All information including images are given with the greatest care. Still, it is appropriate to users regardless of the test the suitability of each product for their own purposes. Tech-Masters is not liable for the completeness and accuracy of information and refuses warranty for your specific use. The guarantee, which Tech-Masters products provide, relates only to the standard conditions of sale of this product. In no case Tech-Masters can be held responsible for incidental damages, or damages for improper use or sale of the product to another customer.

