

ELECTRO CLEANER N

DIELECTRIC SOLVENT FOR ELECTRONICS



COMPATIBILITY

PLASTICS

Description	5 minutes	1 hour	24 hours	100 hours
Epoxy glass	5	5	5	5
Backelite (phenolic)	5	5	5	5
LDPE	3	2	1	0
HDPE	5	5	5	5
Polycarbonate	0	0	0	0
Polybutadiene tereftalate	5	5	5	5
Polyethylene tereftalate	5	5	5	5
Polymethylmetacrylate	0	0	0	0
Polypropilene	4	3	3	2
Polystyrene	0	0	0	0
PTFE	5	5	5	5
PVC hard	0	0	0	0
PVF	5	5	5	5

ELASTOMERS

Description	5 minutes	1 hour	24 hours	100 hours
Acrylonitrile/butadiene n° 418	4	3	1	5
Ethylene/propylene EPR	4	3	2	2
Isobutene/isoprene	4	3	2	1
Neoprene	4	3	2	1
Fluoroelastomer (kairez)	5	5	5	5
Viton A	4	3	2	2
Viton B	4	3	2	2
Buna N	4	3	2	2
Clorosulfonate PE (hypalon)	0	0	0	0
Silicones	0	0	0	0

Legend

- 5 no aggression
- 4 it leaves surface slightly opaque
- 3 slightly surface swelling
- 2 total swelling
- 1 partial fade
- 0 total fade

