



# Technical Information

## TECHNO STICK

	Aluminium	Water	Wood	Copper	Steel/Metal
Shore Hardness D	87	82	80	82	87
Curing temperature	6 to 30°C	6 to 30°C		6 to 30°C	
Shear strength (DIN 53283)	4,5 N/mm <sup>2</sup>	6 N/mm <sup>2</sup>	5,5 N/mm <sup>2</sup>	7 N/mm <sup>2</sup>	4,5 N/mm <sup>2</sup>
Temperature resistance	-50 to 180°C (short 300°C)	-50 to 120°C	-50 to 180°C (short 300°C)	-50 to 120°C	-50 to 180°C (short 300°C)
Thermal conductivity	0,65 W/m-k	0,5 W/m-k	0,3 W/m-k	0,7 W/m-k	0,6 W/m-k